Kiehl-Legnodur-Titan 2.0

Satin-matt 2-component permanent coating

- Varnish-like drying, plasticiser-free polyurethane emulsion polish
- Coat thickness up to 25 µm
- Certified to DIN 18032, DIN EN 13036 and DIN EN 14904
- Report to DIN 51130 confirming slip-resistance rating R9 available
- Hard-wearing, easy to clean protective film
- Maintenance of the coating after dry cleaning
- The film cannot be removed by wet stripping
- Outstanding film-forming properties
- High chemical resistance, e.g. against hand disinfectants



PCR - post consumer recycled plastic

DIN 18032

Area of application

For coating of wooden floors which have been treated with wood oils or sealings, resilient floorings which can be coated as well as screed floorings.

Application

Please test on a small inconspicuous spot before first application. The surfaces must be clean, release-agent free and properly prepared to ensure faultless adhesion and appearance. Before application, Kiehl-Legnodur-Titan 2.0 (1st component) must be mixed with the second component Kiehl-Durator. Shake immediately. Allow to rest for 5 minutes. The resulting 2-component coating can be used for 6 hours. Close canister immediately after use. Avoid draughts during use and drying.

Preparation of the surface:
Dry clean parquet surfaces before coating (use Kiehl-Legno-Pad Xtreme). Resilient floor coverings must be stripped (Veroclean, 3 L to 8 L of water). Resilient floorings already coated with Kiehl-Legnodur must be dry cleaned using a Kiehl-Legno-Pad Xtreme. Accruing dust must be removed.

Coating:
Depending on the absorbency of the surface, 2–3 applications at intervals of approx. 90 minutes.
After preparing the surfaces, apply a thin coat of undiluted product to the clean floor using a flat mop or waxer. If necessary, carry out intermediate sanding using a Kiehl-Woodmaster-Pad-Fine after applying the first layer. If there is more than 24 hours drying time between the applications, an intermediate sanding with Kiehl-Legno-Pad Xtreme must be carried out. Consumption: 30.0 ml/m^2 per application.



Note

Kiehl accepts no liability or responsibility for damage caused as a result of incorrect use or application of the product. Not a consumer product according to (EU) 2019/771 Art. 2! For professional use only! Protect from frost.

Ingredients

Synthetic dispersions, free from metal salts, water-soluble solvents, preservatives.
pH value (concentrate): approx. 7.5

Classification

Classification (in concentrate): EUH208 Contains Benzisothiazolinone, Methylisothiazolinone, Methylchloroisothiazolinone. May produce an allergic reaction.

Art. No.	Packaging unit (PU)	Numbers of PU per pallet
j1904115	Carton of 5 L PCR canister + 100 ml Kiehl-Durator	112

www.kiehl-group.com